

Used Products

IMPLANT - Abutment made of zirconium oxide - Crown - Oxide ceramics - Retentive abutment shape - Posterior tooth - Vivaglass CEM

☐ VivaglassCEM PL

VivaglassCEM PL is a highly translucent self-curing, radiopaque glass-ionomer cement



☐ OptraStick

Application instrument that features a flexible adhesive tip



☐ Telio CS Inlay

Temporary light-curing filling material for deep inlay preparations with parallel walls and sealing of implant screw access holes



☐ OptraGate

Allows lips and cheeks to be retracted completely and ensures relative isolation



☐ Ivoclean

The universal cleaning paste Ivoclean effectively cleans the bonding surfaces of prosthetic restorations after intraoral try-in



☐ OptraPol

OptraPol is excellently suitable for finishing and polishing all popular composite materials in a single step



☐ Cervitec Plus

The protective varnish containing chlorhexidine and thymol protects exposed root surfaces and controls bacteria



Flowchart Vivaglass CEM

IMPLANT - Abutment made of zirconium oxide - Crown - Oxide ceramics - Retentive abutment shape - Posterior tooth - Vivaglass CEM

1 Preoperative situation




The abutment is screwed in place.

2 The restoration is tried in



The permanent restoration is tried in. At this stage, the shade, accuracy of fit and occlusion of the restoration are checked.

3 The screw access opening is cleaned and sealed.



The screw access opening is thoroughly rinsed with water spray and dried with oil-free air. Subsequently, the screw access opening is sealed with cotton wool or a foam pellet and **Telio CS Inlay**. For all further treatment steps, relative isolation of the operating field, e.g. with **OptraGate**, is indispensable. A retraction cord may optionally be placed.

4 The restoration is pretreated



The inner surfaces of the restoration are sandblasted (e.g. **IPS e.max ZirCAD**, 1 bar, Al_2O_3 100 μm or as directed by the manufacturer of the restorative materials).

5 Vivaglass CEM is mixed and applied



The **Vivaglass CEM** powder and liquid are mixed in a 1:1 ratio.



The luting material is applied to the restoration with a spatula or brush.

6 The restoration is seated and excess cement is removed




The restoration is seated and held in place using light constant pressure.



Once the cement has completely set, excess is removed e.g. with an implant scaler. The setting time is 4-6 minutes.

7 The completed restoration is finished



Proximal areas are adjusted with finishers and polishers. The occlusion and functional movements are checked and adjusted if necessary. The restoration margins are polished with polishers (**OptraPol**) or discs.

8 Follow-up care



A thin layer of **Cervitec Plus** is applied where it is needed with the help of a Vivadent applicator or a brush. The varnish sets by itself or with the application of a stream of air.